



Europäisches
Patentamt

European
Patent Office

Office européen
des brevets

10/031054

REC'D 18 SEP 2000

WIPO

PCT

Bescheinigung

Certificate

Attestation

Die angehefteten Unterlagen stimmen mit der ursprünglich eingereichten Fassung der auf dem nächsten Blatt bezeichneten europäischen Patentanmeldung überein.

The attached documents are exact copies of the European patent application described on the following page, as originally filed.

Les documents fixés à cette attestation sont conformes à la version initialement déposée de la demande de brevet européen spécifiée à la page suivante.

Patentanmeldung Nr. Patent application No. Demande de brevet n°

99202343.2

**PRIORITY
DOCUMENT**
SUBMITTED OR TRANSMITTED IN
COMPLIANCE WITH RULE 17.1(a) OR (b)

Der Präsident des Europäischen Patentamts:
Im Auftrag

For the President of the European Patent Office

Le Président de l'Office européen des brevets
p.o.

I.L.C. HATTEN-HECKMAN

DEN HAAG, DEN
THE HAGUE, 05/09/00
LA HAYE, LE



Europäisches
Patentamt

European
Patent Office

Office européen
des brevets

Blatt 2 der Bescheinigung
Sheet 2 of the certificate
Page 2 de l'attestation

Anmeldung Nr.
Application no.
Demande n° 99202343.2

Anmeldetag
Date of filing
Date de dépôt 16/07/99

Anmelder
Applicant(s)
Demandeur(s)
Rockwool International A/S
2640 Hedehusene
DENMARK

Bezeichnung der Erfindung
Title of the invention
Titre de l'invention

Resin for a mineral wool binder comprising the reaction product of an amine with a first and second anhydride

In Anspruch genommene Priorität(en) / Priority(ies) claimed / Priorité(s) revendiquée(s)

Staat
State
Pays

Tag
Date
Date

Aktenzeichen
File no.
Numéro de dépôt

Internationale Patentklassifikation
International Patent classification
Classification internationale des brevets

C03C25/24, C03C25/26

Am Anmeldetag benannte Vertragsstaaten
Contracting states designated at date of filing AT/BE/CH/CY/DE/DK/ES/FI/FR/GB/GR/IE/IT/LI/LU/MC/NL/PT/SE
Etats contractants désignés lors du dépôt

Bemerkungen
Remarks
Remarques

The application was transferred from the original applicant:
TIDIS B.V. to the above mentioned applicant

**RESIN FOR A MINERAL WOOL BINDER COMPRISING THE REACTION
PRODUCT OF AN AMINE WITH A FIRST AND SECOND ANHYDRIDE**

The invention relates to a compound or salts thereof suitable for use as a binder for mineral fibres, i.e. men made vitreous fibres (MMVF), for example glass slag or stone wool, i.e. mineral wool, in particular Rockwool, a binder composition comprising such a compound, a process for providing said compound and composition, a mineral fibre product provided with such a binder and the use of said compound and composition as a mineral fibre binder.

Phenol and formaldehyde resins which are mainly used as binders for glass or stonewool release toxic substances during curing, for example formaldehyde.

During application and curing of the binders, after provision thereof to the mineral fibres, phenol, formaldehyde and ammonia are released. From an environmental point of view this is undesirable.

Furthermore during application, mostly by spraying, of the binder onto the spun glass or stone fibres a large amount of binder is lost, which is almost impossible to recover for re-use.

A formaldehyde and phenol free resin suitable for a binder for mineral wool fibres is described in the patent application PCT/NL99/00029 from the applicant.

According to a first aspect of the present invention there is provided a resin for a binder suitable for mineral fibres such as glass or stone wool according to claims 1-6.

The inventors have found that the resin obtained on mixing together different cyclic anhydrides, preferably an aliphatic anhydride and an aromatic anhydride in a polymer free mixture with an amine,

provides a resin suitable for a mineral wool binder, which has desirable curing times.

The inventors theorize that the increased curing speed may not only be related to the combined use of cyclic anhydrides, but also to the adjustment of the pH, preferably to between 2.5 and 4.2, by employing aromatic carboxylic acids. These carboxylic acids are more acidic than aliphatic ones. Trimellitic anhydride is even more acidic due to the presence of an extra electron withdrawing group.

According to a second aspect of the present invention there is provided a binder according to claims 7-12.

According to a further aspect of the present invention there is provided a mineral fibre product according to claim 13.

According to yet a further aspect of the present invention there is provided a process for providing a polymer free resin for a binder suitable for binding mineral fibre products according to claim 14.

According to yet another use of the present invention there is provided the use of the above referred to resin in a mineral wool binder.

The invention will now be further clarified by way of the following description with reference to the examples.

Three binder compositions were made up according to the Mol.ratios as shown in table 1, whereby various accelerators were added to these compositions (see column 3 of table 1).

Example 1

Binder 1

A double jacketed glass reactor, heated with hot water, provided with a magnetic stirrer and a reflux condenser is used.

3

158 g diethanolamine (DEA) and 100 g water were brought into the reactor and heated to 70°C.

Then 228 g tetrahydrophthalic anhydride (THPA) was added allowing the temperature to raise to 90°C. This gives molratio DEA:THPA = 1:1

The reaction time was allowed to be 120 minutes before cooling of the resin.

Another resin with molratio DEA (158 g) : THPA (365 g) = 1:1,4 was made in the same way.

The binder solution was made by diluting the resin to about 40% solids with water. When accelerators were used they were added to the binder solution when it was ready for testing.

15 Binder 2

The same equipment and procedure were used as for binder 1, except that phthalic anhydride (PTA) was added to the mixture when all THPA was dissolved.

3 resins were made with different molratios of the compounds.

Molratios used are:

DEA (158 g) : THPA (228 g) : PTA (89 g) = 1:1:0,4

DEA (158 g) : THPA (183 g) : PTA (133 g) = 1:0,8:0,6

25 DEA (158 g) : THPA (137 g) : PTA (178 g) = 1:0,6:0,8

The binder solution was made by diluting the resin to about 40% solids with water. When accelerators were used they were added to the binder solution when it was ready for testing.

Binder 3

The same equipment and procedure were used as for binder 1, except that trimellitic anhydride (TMA) was added to the mixture when all THPA was dissolved.

4 resins were made with different molratios of the compounds.

5

Table 1

	Composition of binder	Mol.ratios	Accelerator-% of solids	Flowtime minutes	Mechanical strength	
					Unaged	Aged
5	1) DEA:THPA	1:1	none	>10	4,80	2,55
			Citric acid-0,3-2%	5		
			Hypophos. acid-0,3-2%	5		
		1:1,4	none	>10		
10			Citric acid-3-4%	7		
			Hypophos.acid-1-2%	6		
			Na-phosphinat-4%	7		
	2) DEA:THPA:PTA	1:1:0,4	none	5	5,89	2,77
			Na-phosphinate-4%	7		
15			Hypophos.acid-1%	5		
		1:0,8:0,6	none	5	3,05	1,04
			Na-phosphinat-4%	7		
			Hypophos acid-1%	5		
		1:0,6:0,8	none	5		
20			Na-phosphinate-4%	7		
			Hypophos.acid-1%	5		

Table 1 [continued]

5	3) DEA:THPA:TMA	1:1,3:0,1	none	4	8,55	2,77
			Hypophos.acid-0,5-1%	4		
		1:1,2:0,2	none	4	6,88	2,07
			Hypophos.acid-0,5-1%	4		
		1:1:0,4	none	5	3,81	1,25
10			Hypophos acid-0,2-1%	4		
			Na-phosphinate-4%	2		
		1:0,8:0,6	none	3	2,62	
			Hypophos.acid-0,5-1%	3		

Conclusion:

Addition of aromatic anhydrides as PTA and TMA
 15 reduce the "flowtime" with a factor 2.

Accelerators as citric acid, phosphonic acid or
 sodiumphosphinate reduce the "flowtime" by a factor 2
 when THPA is used as the only anhydride. Accelerators do
 not decrease the "flowtime" further when aromatic
 20 anhydrides are in the formulation. They themselves act as
 an accelerator.

7

Example 3 Storage stability of resin made at 90°C
reaction temperature compared to 70°C

The preferred reaction temperature is 90 to 100°C using formulations containing up till 30% W/W water of the weight of anhydride. The water is mixed with the diethanolamine before the anhydride is added.

Using lower reaction temperature may cause precipitation if stored more than 2 weeks at solids higher than 75%.

10 If diluted at once with water to solids below 60% no precipitation is observed.

From a storage and transport point of view it is advantageous to have as high solids content as possible.

15

Example 4 Batch reactor

The reflux cooling is started.

20 40 kg melted diethanolamine (60°C) is pumped into the reactor.

The stirrer is started, 24 kg demineralized water is added and the temperature raised to 70°C.

25 80 kg tetrahydrophthalic anhydride is added portion wise over approximate 15 minutes, not allowing the temperature to exceed 95°C. The reactor is cooled if necessary.

The reaction temperature is held at 90-95°C for 15 minutes after all the anhydride is dissolved.

30 After 15 minutes the resin was cooled to room temperature.

The resin contained approximately 80% solids determined at 200°C.

35

Example 5 Continuous reactor

5 A double jacketed stainless steel tube reactor with a static mixer at the inlet is used. The temperature in the reactor is steered by cooling or heating with water.

Diethanolamin at 60°C and a water suspension of tetrahydrophthalic anhydride is pumped into the tube reactor and mixed when passing the static mixer. The
10 temperature is raised and adjusted to 90-95°C. Diethanolamin and the water suspension of tetrahydrophthalic anhydride are pumped from separate tanks in pre-set ratio for the resin formulation.

15 The flow of the components are adjusted so that it takes approximate 20 minutes after the reaction mixture has passed the static mixer, and left the reactor.

Volume of the tube reactor is 33 litres.

20 Flow is approximately 100 kg per hour, or 20 kg diethanolamine and 80 kg suspension containing 40 kg tetrahydrophthalic anhydride in 40 kg water, all per hour.

When the reaction mixture leaves the tube
25 reactor it may be diluted with water to 30% solids, cooled to room temperature and is ready for use.

Other additives as silane coupling agent, curing accelerators, hydrophilic or hydrophobic agent etc. may be added to the binder "on stream" after the
30 reactor.

The invention is not limited to the above description; the requested rights are rather determined by the following claims.

CLAIMS

1. Resin for a binder suitable for mineral fibers such as glass or stone wool, said resin comprising the reaction product of a polymer free mixture of an amine with a first anhydride and a second anhydride, 5 characterized in that the first and second anhydrides are different anhydrides.

2. Resin for a binder suitable for mineral fibers such as glass or stone wool according to claim 1, wherein the first anhydride is a cyclic, preferably an 10 aliphatic anhydride and wherein the second anhydride is a cyclic, preferably an aromatic anhydride.

3. Resin comprising a polymer free mixture for a binder, said resin comprising the reaction product of a cyclic anhydride and an amine, at a pH, preferably being 15 between 2.5 and 4.2, said pH being predetermined to positively influence the curing speed of the resin.

4. Resin according to any of the claims 1-3, wherein the aliphatic anhydride comprises tetrahydro phthalic anhydride, and/or hexahydrophthalic anhydride, 20 methyltetrahydrophthalic anhydride, succinic anhydride, nadic anhydride, maleic anhydride, glutaric anhydride.

5. Resin according to any of the claims 1 to 4 wherein the aromatic anhydride comprises phthalic anhydride and trimellitic anhydride and/or pyromellitic 25 dianhydride, methylphthalic anhydride.

6. Resin according to any of the preceding claims, wherein the amine, being a N-substituted beta hydroxy alkylamine, is selected from the group (di)ethanolamine, 1-(m)ethylethanolamine, n-butyl- 30 ethanolamine, 1-(m)ethylisopropanolamine, 3-amino-1,2-propanediol, 2-amino-1,3-propanediol, tris(hydroxymethyl)aminomethane, most preferably diethanolamine.

7. Binder for mineral fibres such as glass or stone wool, said binder comprising a resin according to any of the claims 1-6.

8. Binder comprising a resin according to claim 5 7 further comprising an accelerator and one or more resin additives such as aminopropyl siloxane to improve adhesion to glass, thermal and UV stabilizers, surface active compounds, fillers such as clay, silicates, magnesiumsulfate and pigments such as titanium oxide, 10 hydrophobising agents such as fluorine compounds, oils, minerals and silicone oils.

9. Binder according to claim 8 wherein the accelerator is selected from the group comprising sodium phosphinate, phosphinic acid, citric acid, adipic acid 15 and β -hydroxyalkylamid.

10. Binder according to claims 8 or 9 wherein the additives are selected from the group comprising mono-, di-, and polysaccharides, such as sucrose, glucose syrup, modified starch, starch urea dicyandiamid, 20 polyglycols, acrylics, furfural, carboxymethyl cellulose and cellulose, or polyvinyl alcohol.

11. Binder according to any of the claims 7-10 or resin according to any of the claims 1-6, wherein the concentration of aliphatic anhydrides is greater than the 25 concentration of aromatic anhydrides.

12. Binder for mineral fibers, particularly mineral wool comprising a resin according to any of the preceding claims 1-6, which has been cured.

13. Mineral fibre product, specifically a 30 mineral wool product, bound by a cured binder according to claim 12, or claims 7-11.

14. Process for providing a polymer free resin for a binder suitable for binding mineral fibre products, said process comprising the steps of mixing together 35 under reaction conditions an amine with a first anhydride and a second different anhydride, these preferably being an aliphatic, cyclic anhydride and a cyclic aromatic anhydride respectively.

3

15. Use of a resin according to any of the
claims 1-6 in a binder according to claims 7-11.

1

ABSTRACT

Resin for a binder suitable for mineral fibers such as glass or stone wool, said resin comprising the reaction product of a polymer free mixture of an amine with a first anhydride and a second anhydride, 5 characterized in that the first and second anhydrides are different anhydrides.